



(19)

(11) Publication number:

08012378 A

Generated Document.

PATENT ABSTRACTS OF JAPAN

(21) Application number: 06149274

(51) Intl. Cl.: C03C 17/34 B60J 1/00 E06B 3/02

(22) Application date: 30.06.94

(30) Priority:

(43) Date of application
publication: 16.01.96(84) Designated contracting
states:

(71) Applicant: NISSAN MOTOR CO LTD

(72) Inventor: SHIBATA ITARU
NISHIDE RIICHI

(74) Representative:

**(54) HEAT RAY CUT-OFF
GLASS AND ITS
PRODUCTION**

(57) Abstract:

PURPOSE: To obtain a heat ray cut-off glass by laminating a 1st dielectric film on a glass substrate as a 1st layer from the substrate side, a tungsten oxide film thereon as a 2nd layer and a 2nd dielectric film further thereon as a 3rd layer.

CONSTITUTION: A transparent glass substrate is defatted, cleaned and dried

and arranged in a vacuum vessel of a sputtering device. Next, the 1st dielectric film of silicon oxide having 2-300nm thickness and refractive index of 1.4-1.9 is film-formed on the glass substrate as the 1st layer by evacuating the vacuum vessel to vacuum and introducing Ar/O₂ mixed gas to a silicon oxide target for sputtering. Next, the tungsten oxide film having 2-300nm thickness, refractive index of 1.9-2.8 and O/W ratio of 2.60-2.98 is film-formed as the 2nd layer by sputtering the Ar/O₂ mixed gas to a tungsten oxide target. Further, the 2nd dielectric film of silicon oxide having 2-300nm thickness and refractive index of 1.4-1.9 is film-formed as the 3rd layer by sputtering the Ar/O₂ mixed gas to the silicon oxide target to obtain the heat ray cut-off glass.

COPYRIGHT: (C)1996,JPO